

TECHNICAL INFO	Scientific Name	Density kg/m3	Hardness	Under-floor heating
WENGE	Millettia Laurenti	870	4.2	Suitable
MAPLE	Acer Sacharum	650	3	Not Suitable
IROKO	Chlorophora excelsa	660	3.5	Suitable
MERBAU	Intsia Bijuga	700	4.1	Suitable
DOUSSIE	Azelia Africana	800	4	Suitable
WALNUT	Juglans Regia	720	2.5	Suitable
TEAK	Tectona Grandis	680	3.5	Suitable
OAK	Quercus Robur	780	4.1	Suitable
BEECH	Fagus Sylvatica	730	4.5	Not Suitable
MAHOGONY	Entandrophragma cylindrioum	690	3.5	Not Suitable, risk
ASH	Fraxinus excelsior	611	3.5	Not Suitable, risk
CABREUVA	Myrocarpus frondosus	920	4.5	Suitable